

<b>Name</b>	<b>Chemical formula</b>	<b>ZrO<sub>2</sub>(+HfO<sub>2</sub>)</b>	<b>CaO</b>	<b>PSD (d<sub>50</sub>)</b>
LUVOZIRC® CASZ	CaO - ZrO <sub>2</sub>	94.5 - 95.5 %	4.5 - 5.5 %	1 - 10 μm
LUVOZIRC® CASZ P1	CaO - ZrO <sub>2</sub>	> 94 %	3.5 - 4.2 %	1 - 10 μm
LUVOZIRC® CASZ P2	CaO - ZrO <sub>2</sub>	> 95 %	3.0 - 4.2 %	1 - 10 μm
LUVOZIRC® CASZ P3	CaO - ZrO <sub>2</sub>	> 91 %	7.0 - 7.8 %	1 - 10 μm