

Name	Chemical formula	Y₂O₃	BET	PSD (d₅₀)
LUVOZIRC® YSZ 3mol	Y ₂ O ₃ - ZrO ₂	5.10 - 5.30 %	5 - 10/10 - 20 m ² /g	0.3 - 0.5 μm
LUVOZIRC® YSZ 4,5mol	Y ₂ O ₃ - ZrO ₂	7.8 - 8.0 %	5 - 10/10 - 20 m ² /g	0.3 - 0.5 μm
LUVOZIRC® YSZ 8mol	Y ₂ O ₃ - ZrO ₂	13.0 - 15.0 %	5 - 10/10 - 20 m ² /g	0.3 - 0.5 μm